

Kohlearten				Wasser- gehalt (%)	Energie- gehalt af* (kJ/kg)	flüchtige Anteile waf** (%)
UN-ECE	USA (ASTM)	Deutschland (DIN)				
Peat	Peat	Torf		75	6,700	
Ortho- Lignite	Lignite	WEICHBRAUNKOHLE				
Meta- Lignite		Sub- bituminous Coal	Mattbraunkohle		35	16,500
Subbitum. Coal	Glanzbraunkohle		25		19,000	
Bituminous Coal	High Volatile Bituminous Coal	Flammkohle	steinkohle	10	25,000	45
		Gasflammkohle		40		
		Gaskohle		35		
	Medium Vol. Bitumin. Coal	Fettkohle		36,000		28
		Eßkohle		Kokskohle		19
	Low Vol. Bitumin. Coal					14
Anthracite	Semi- Anthracite	Magerkohle		3	36,000	10
	Anthracite	Anthrazit				

af \* = aschefrei

waf \*\* = wasser- und aschefreie Substanz